

TIMKEN PILLOW BLOCK GREASE

Lubricating Grease

Part Numbers

GR220C-00000	1 14-Ounce Cartridge
GR220C-90001	10 14-Ounce Cartridge
	40 14-Ounce Cartridge
GR220P-00000	1 35-Pound Pail
GR220K-00000	1 120-Pound Keg
GR220D-00000	1 400-Pound Drum

Product Description and Intended Use

TIMKEN Pillow Block Grease is an NLGI No. 2 shear stable polyurea thickened grease specifically designed for the lubrication of moderate to high speed ball bearings in pillow block applications. Timken Pillow Block grease is highly resistant to oxidation and has excellent corrosion resistance even in the presence of salt water. It is also recommended for moderate to high speed ball bearings operating in environments that are sensitive to noise.

Product Application

TIMKEN Pillow Block Grease can be applied from ambient temperatures of - 30° F to + 325° F (- 34° C to + 163° C) depending on lubrication system design and method of application. TIMKEN Pillow Block Grease has an operating range of - 40° F to + 325° F (- 40° C to + 163° C) once in the application. Follow equipment manufacturer's recommendations concerning lubrication frequencies.

Compatibility of Grease

TIMKEN Pillow Block Grease is generally compatible with calcium sulfonate and polyurea thickened greases. TIMKEN recommends that all grease be removed from the application prior to changing greases. Then the lubrication interval is reduced by half for the first lubrication cycle before resuming the normal lubrication interval.

Handling and Storage

Store in a dry area away from heat and open flame. See Material Safety Data Sheet for more information.

Shipping and Disposal Information

Follow governmental regulations pertaining to the shipping and disposal of this product. Do not reuse container. See Material Safety Data Sheet for more information.

The technical data contained herein is intended for reference only. Chemtool Incorporated specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Chemtool Incorporated's products and disclaims any liability for consequential or incidental damages of any kind whatsoever.

TIMKEN® PILLOW BLOCK GREASE

Product Specifications – Typical

Color	Dark Blue
NLGI Grade	2
Thickener Type	Polyurea
Penetration, Unworked, ASTM D 217	220 Min.
Penetration, Worked 60 Strokes, ASTM D 217	265-295
Penetration Change, 100000 Strokes, ASTM D 217	310-360
Wheel Bearing Leakage, ASTM D 1263	5 Grams Max.
Dropping Point, ASTM D 2265	> 260° C
Oxidation Stability, ASTM D 942, 100 hours at 99° C	5
Four-Ball Wear, ASTM D 2266, 40 kg, 1200 RPM, 75° C, Scar mm	0.4
Copper Strip Corrosion, ASTM D 4048	1a
Corrosion Preventive Properties, ASTM D 1743	Pass
EMCOR Corrosion, ASTM D 6138, 10 % Synthetic Seawater	0,0
Oil Separation, ASTM D 1742	0.3
Water Washout, ASTM D 1264, 175° F (79° C), % Loss	2
Bearing Life, ASTM D 3336, 177° C, Hours	> 750
Base Fluid Properties:	
Viscosity @ 100° C, ASTM D 445, Centistokes	9-13
Viscosity @ 40° C, ASTM D 445, Centistokes	100-120
Viscosity Index	95
Flash Point, ASTM D 92	255° C
Pour Point, ASTM D 97	- 15° C

Date: August 18, 2003

Product: TIMKEN Pillow Block Grease